



Toll Free: 87 PERMATEX  
(877-376-2839)

10 Columbus Blvd., Hartford,  
Connecticut 06106

6875 Parkland Boulevard, Solon  
Ohio 44139

## Technical Data Sheet

# Permatex<sup>®</sup> High Temperature Thread Sealant

AAM Revised 06/14

### PRODUCT DESCRIPTION

Permatex<sup>®</sup> High Temperature Thread Sealant is a medium strength anaerobic sealant with PTFE for tapered pipe threads. This sealing compound is of a white, creamy paste consistency. The high lubricating properties of this compound prevents galling on pipe threads and fittings. It will provide immediate low pressure sealing and allow for the readjustment of fittings shortly after assembly. After 72 hours the joint is sealed to pipe burst pressure. This product has a medium solvent resistance and will withstand temperatures to 400°F (204°C). **This product is not recommended for use on plastic piping.**

### PRODUCT BENEFITS

- Resists leakage, vibration loosening, moisture, hydraulic fluids, diesel fuels.
- Lubricates threads for easy assembly and disassembly.
- Will not shred or wear like tapes.
- Parts may be repositioned for up to 24 hours after application.
- Suited for temperatures up to 400°F (204°C).

### TYPICAL APPLICATIONS

- Head bolts into through holes
- Oil PSI sending units/sensors
- Oil and coolant lines
- Fuel fittings
- Rear axle fill plug
- Brake and power steering fittings

### DIRECTIONS FOR USE

1. For best performance, surfaces should be clean and free of grease.
2. Product should be applied to the thread engagement area in sufficient quantity to fill all engaged threads.
3. Use accepted trade practices to assemble and wrench-tighten fittings until proper alignment is obtained.
4. Very large thread sizes may create large gaps, which will affect cure speed and strength.
5. For maximum pressure and solvent resistance, allow at least 24 hours for the product to fully cure before filling and pressurizing system.
6. Fittings assembled with Permatex<sup>®</sup> High Temperature Thread Sealant may be disassembled with normal hand tools.
7. For large pipe diameters (over 1"), heat may be required to disassemble fittings.
8. Fittings may be reused by removing loose sealant residue with a wire brush and reapplying sealant.

### FOR CLEANUP

1. Wipe off any material outside the joint with a dry cloth.
2. Clean hands with Permatex<sup>®</sup> Fast Orange<sup>®</sup> hand cleaner or soap and water.
3. Cured material must be removed with Permatex<sup>®</sup> Gasket Remover.

### PHYSICAL PROPERTIES OF UNCURED MATERIAL

	Typical Value
Chemical Type	Dimethacrylate ester
Appearance	White opaque paste
Odor	Acrid
Specific Gravity, g/ml	1.21
Viscosity (cP)	350,000
Flash Point (T.C.C.) °F	>200
Chemical resistance	Gasoline, oil, water, glycol, hydraulic fluid, freon, transmission fluid, brake fluid

### CURED INFORMATION

(Cured 72 hours @ 75°F)

Pressure Resistance (psi)	10,000
Temperature Range (°F)	-65 to +400
Breakaway torque (in.-lb.)	40
Maximum recommended pipe size	2" NPT

### GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).**

### ORDERING INFORMATION

Part Number	Container Size
59214	6 ml. tube, carded
59235	50 ml. tube, carded

### STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8°C and 28°C (46°F and 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

**NOTE**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex, Inc. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, Inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits.** This product may be covered by one or more United States or foreign patents or patent applications.